



WAX REPORT - LP Super Tour Classic Distance 10km

Date: January 21, 2024

Location: Mount Van Hoevenberg, Lake Placid, NY

Wax Reporter: Drew Gelinias

Snow & Weather Conditions
Thursday, 30% chance of new snow, cold temps, High of 17F, Low of 2F at night.
Friday Partly Cloudy, no new snow. High Temp 12F.
Friday Night, no new snow and cold. Low Temp of -5F.
Saturday Morning, Cloudy, High of 5F. Winds 8 to 10 mph. Temps around zero for first heats.
Saturday Night, -3F. West wind up to 10 mph.
Sunday, Partly Sunny, High of 13F. Will be cooler at race time.
Colder temps will set up tracks perfectly firm and hard. Cloudy conditions will prevent solar melt and ice. If the sun does break out, there may be glazing in the tracks.

Tier 1 - Recommendations	Tier 2 - Recommendations
Glide Wax: HS05 ironed in at 160C. Scraped and brushed.	Glide Wax: TSP05 ironed in at 160C. Scraped and brushed.
Freshen up the kick zone with 120 grit sandpaper.	Topping: TST05 roto corked, then brushed.
Binder: VG035 Binder ironed in the kick zone.	Freshen up the kick zone with 120 grit sandpaper.
VP30 or V20, several thin layers, corked smooth each layer. Allow skis to cool.	Binder: VG035 Binder ironed in the kick zone.
Do not kick wax past the heel location of binding.	VP30 or V20, several thin layers to kick zone and corked smooth each time. Allow skis to cool.
	Do not wax past the heel location of binding.



NOTES: If temperatures increase more rapidly than forecasted, adjust top coat with TS6 liquid.